

200 µm PYROCOAT[®] Step-Index Optical Fiber P/N: CF04406-03



Overview

High OH concentration in these fibers results in efficient power transmission in the wavelength range from high UV through visible light. The all-silica base construction also creates a high damage threshold and high-performance optical properties.

High temperature environments require the use of PYROCOAT® polyimide coating.

Typical Applications

Illumination Laser Surgery Radiation Analysis Sensors UV Fluorescene UV Spectroscopy



200 µm PYROCOAT® Step-Index Optical Fiber P/N: CF04406-03

| Product Specifications | |
|-----------------------------------|----------------------------|
| Product Description | 200 µm PYROCOAT Step-Index |
| Physical Characteristics | |
| Core Diameter | 200 ± 5 μm |
| Cladding Diameter | 220 ± 5 μm |
| Coating Diameter | 250 ± 5 μm |
| Coating Concentricity | ≥ 80% |
| Crimp & Cleave Compatible | No |
| Coating Material | PYROCOAT |
| Optical Characteristics | |
| Туре | Multimode Step-Index |
| Numerical Aperture | 0.22 |
| Attenuation @ 820 nm | ≤ 10 dB/km |
| Water Content | High OH |
| Mechanical and Environmental | |
| Operating Temperature | -65 to +300 °C |
| Short-Term Temperature Excursions | Up to 400 °C |
| Short-Term Bend Radius | ≥ 17 mm |
| Long-Term Bend Radius | ≥ 28 mm |
| Proof Test Level | ≥ 100 kpsi (0.689 GPa) |
| Order by Part Number | CF04406-03 |
| Product Description Code | TCG-MA200H |

OPTIONS: Clad Diameter, Core Diameter, Connectorization, Numerical Aperture, Metalization, Proof Test

NOTE: OFS polyimide optical fibers are known to operate in environments up to 300 °C. Performance is application dependent. Contact our Technical Sales department to discuss your specific application requirements. 1-860-678-6636

For additional information please contact your sales representative.

You can also visit our website at www.ofsoptics.com or call 1-888-fiberhelp (1-888-342-3743) USA or 1-770-798-5555 outside the USA.



Copyright © 2019 OFS Fitel, LLC. All rights reserved, printed in USA.

OFS Marketing Communications Date: 12/19

HCS and PYROCOAT are registered trademarks of OFS Fitel, LLC. OFS reserves the right to make changes to the prices and product(s) described in this document at any time without notice. This document is for informational purposes only and is not intended to modify or supplement any OFS warranties or specifications relating to any of its products or services.