



PRESSURE PIPE

SDR		3/4"	1"	1 1/4"	1 1/2"	2"	3"	4"
333 PSI	OD	1.050	1.315	1.660	1.900	2.375	3.500	4.500
	ID	0.730	0.920	1.160	1.325	1.656	2.440	3.137
SDR7	WALL	0.150	0.188	0.237	0.271	0.339	0.500	0.643
	WT/FT	0.190	0.290	0.460	0.610	0.950	2.060	3.400
250 PSI	OD	1.050	1.315	1.660	1.900	2.375	3.500	4.500
	ID	0.818	1.023	1.292	1.478	1.847	2.722	3.500
SDR9	WALL	0.117	0.146	0.184	0.211	0.264	0.389	0.500
	WT/FT	0.150	0.230	0.370	0.490	0.760	1.650	2.720
200 PSI	OD	1.050	1.315	1.660	1.900	2.375	3.500	4.500
	ID	0.860	1.075	1.358	1.554	1.943	2.864	3.682
SDR11	WALL	0.095	0.120	0.151	0.173	0.216	0.318	0.409
	WT/FT	0.120	0.190	0.310	0.410	0.640	1.400	2.250
160 PSI	OD	0.000	1.315	1.660	1.900	2.375	3.500	4.500
	ID	0.000	1.121	1.414	1.618	2.023	2.982	3.834
SDR 13.5	WALL	0.000	0.097	0.123	0.141	0.176	0.259	0.330
	WT/FT	0.110	0.160	0.260	0.340	0.530	1.160	1.910
125 PSI	OD	0.000	0.000	0.000	0.000	2.375	3.500	4.500
	ID	0.000	0.000	0.000	0.000	2.080	3.088	3.970
SDR 17	WALL	0.000	0.000	0.000	0.000	0.140	0.206	0.265
	WT/FT	0.000	0.000	0.000	0.000	0.420	0.910	1.510

- IPS
- OD CONTROLLED
- HEAT FUSION
READY

 Raw
Material

Manufactured using only virgin
4710 resin and NSF approved
master batch (colorant)

 **Conformance**

NSF 61, ASTM D3035
AWWA C901, C906

